



SRI Concrete Products
 2515 Commerce Dr.
 Rock Hill, SC 29730
 Ph. 803-327-6880

Technical Data Sheet for SRI Stampable Overlay

SRI Concrete Product's- Stampable Overlay is a single component polymer modified cement based product that is ideal for stamp work or for re-surfacing old or damaged concrete. It is not intended as a thin finish or "skim" coat. SRI's Stampable Overlay should be applied at a depth of at least 1/4 inch. Contact: SRI Concrete Products for other products for other uses.

PHYSICAL DATA- Finished product using 1 gallon of water per 60 lb. bag

Initial Setting Time (ASTM C-266) 40-60 min.
 Final Setting Time (ASTM C-266) 75-90 min.
 Coverage per 50 lb. 20 sq ft at approx ¼ in.
 Flow (ASTM C-157) 140% (ASTM C-928 min 100%) Expansion,
 in water (ASTM C-157) < 0.10% (ASTM C-928 min + 0.15%)
 Contraction, with drying (ASTM C-157) ...< 0.10%(ASTM C-928 min – 0.15%)

Compressive Strength		ASTM C-109
3 hours after set	1000 psi (6.9 Mpa)	1000 psi (6.9 Mpa)
1 day.....	2800 psi (16.1 Mpa)	2000 psi (13.9 Mpa)
7 days	5200 psi (35.8 Mpa)	4000 psi (27.6 Mpa)
28 days	7000 psi (48.3 Mpa)	4000 psi (27.6 Mpa)

Freeze/Thaw 25 cycles- none/negligible

NOTICE: This product contains Portland cement and silica. Use a NIOSH 95 dust respirator (or better). Wear safety goggles; avoid eye and excessive skin contact. If eye contamination occurs flush with water for 15 minutes, and seek medical attention.

WARRANTY DISCLAIMER: The information contained within is accurate to the best of our knowledge. SRI has no control over the jobsite or use of its products, therefore no warranty or guarantee is implied nor can be assumed beyond the replacement of product. No person has the authority to override this warranty, without written consent from SRI Concrete Products.